



*Institute of Paper Science and Technology
Atlanta, Georgia*

IPST Technical Paper Series Number 796

Intrinsic Metal Binding Capacity of Kraft Black Liquor Lignins

J.A. Werner, A.J. Ragauskas, J.E. Jiang

June 1999

Submitted to
Journal of Wood Chemistry and Technology

Copyright® 1999 by the Institute of Paper Science and Technology

For Members Only

INSTITUTE OF PAPER SCIENCE AND TECHNOLOGY PURPOSE AND MISSIONS

The Institute of Paper Science and Technology is an independent graduate school, research organization, and information center for science and technology mainly concerned with manufacture and uses of pulp, paper, paperboard, and other forest products and byproducts. Established in 1929, the Institute provides research and information services to the wood, fiber, and allied industries in a unique partnership between education and business. The Institute is supported by 52 North American companies. The purpose of the Institute is fulfilled through four missions, which are:

- to provide a multidisciplinary education to students who advance the science and technology of the industry and who rise into leadership positions within the industry;
- to conduct and foster research that creates knowledge to satisfy the technological needs of the industry;
- to serve as a key global resource for the acquisition, assessment, and dissemination of industry information, providing critically important information to decision-makers at all levels of the industry; and
- to aggressively seek out technological opportunities and facilitate the transfer and implementation of those technologies in collaboration with industry partners.

ACCREDITATION

The Institute of Paper Science and Technology is accredited by the Commission on Colleges of the Southern Association of Colleges and Schools to award the Master of Science and Doctor of Philosophy degrees.

NOTICE AND DISCLAIMER

The Institute of Paper Science and Technology (IPST) has provided a high standard of professional service and has put forth its best efforts within the time and funds available for this project. The information and conclusions are advisory and are intended only for internal use by any company who may receive this report. Each company must decide for itself the best approach to solving any problems it may have and how, or whether, this reported information should be considered in its approach.

IPST does not recommend particular products, procedures, materials, or service. These are included only in the interest of completeness within a laboratory context and budgetary constraint. Actual products, procedures, materials, and services used may differ and are peculiar to the operations of each company.

In no event shall IPST or its employees and agents have any obligation or liability for damages including, but not limited to, consequential damages arising out of or in connection with any company's use of or inability to use the reported information. IPST provides no warranty or guaranty of results.

The Institute of Paper Science and Technology assures equal opportunity to all qualified persons without regard to race, color, religion, sex, national origin, age, disability, marital status, or Vietnam era veterans status in the admission to, participation in, treatment of, or employment in the programs and activities which the Institute operates.

INTRINSIC METAL BINDING CAPACITY OF KRAFT BLACK LIQUOR LIGNINS

John Werner and Arthur J. Ragauskas
Institute of Paper Science and Technology
500 10th St., NW, Atlanta, GA 30318

Jian E. Jiang
Ahlstrom Machinery Inc.
Glens Falls, NY 12801-3686

ABSTRACT

The metal chelation properties of kraft black liquor lignins were examined for a series of kraft pulps. The addition of purified kraft black liquor lignins to pulp fibers was shown to result in the removal of 20 to 40% of nonprocess elements, such as Mn, Mg, and Ca, in pulp. The effects of concentration and type and amount of black liquor lignin applied were explored. These studies illustrate that differences in the black liquor lignin applied greatly affect the metal removal from pulp. Factors such as extent of delignification and cooking technology influence metal removal properties. In addition, we have demonstrated that a correlation exists between metal removal and the content of carboxylic acids and condensed phenolics in the black liquor lignin applied.

INTRODUCTION

As modern kraft pulping and bleaching operations are developed it is becoming increasingly apparent that these technologies need to have minimal impact on their surrounding environment. One of the key technologies being developed to address this concern reduces the fresh water usage in kraft pulping, bleaching, and papermaking operations.¹ Minimization of mill water usage is

critically dependent on controlling organic and inorganic materials that accumulate in process streams during the production of pulp and paper. Process control of inorganic materials that are not pulping or bleaching chemicals – frequently referred to as nonprocess elements (NPEs), is a rapidly developing field of research. Nonprocess elements commonly include aluminum, barium, calcium, chloride, iron, potassium, magnesium, manganese, and silicon.^{2,3} Mill control of NPEs requires several control strategies; for example, chloride and potassium are very water soluble and difficult to purge from aqueous process streams.⁴ Other elements such as calcium and barium have distinct solubility profiles that can lead to scaling in the bleach plant or recovery cycle.⁵ Finally, other elements like iron and manganese can detrimentally impact the performance of oxygen-based bleaching agents.⁶ In summary, the control of NPEs is an important component of modern pulp manufacturing facilities and additional fundamental studies are needed to provide a sound basis from which new technologies can be developed.

The incoming wood supply is the principal source of most NPEs for kraft pulping operations. Throughout the pulping, bleaching, and papermaking operations NPEs are constantly being fractionated between the fiber and surrounding water. Clearly, the kraft pulping process serves as the first point at which NPEs can be fractionated from the fiber. Under the hot alkaline conditions of pulping, the fiber is able to act as a chelant, retaining certain metals and exchanging others for sodium. It is generally believed that a variety of functional groups in the pulp can bind NPEs, including carboxyl groups from lignin, hexenuronic acid groups, catechols, and phenoxy groups. Several research groups have begun to make significant advances in modeling this process.^{7,8} Recently, we examined the metal binding capacity for a series of well-characterized kraft black liquor lignins.⁹ These studies suggested that there was a correlation between the amounts of carboxyl and condensed phenolics present in

conventional kraft black liquor lignins and their metal binding capacity. These results were tentatively attributed to the potential bidentate metal binding capacity of these two functional groups, as shown in Figure 1. This paper further extends our fundamental investigations into the metal binding capacity of kraft black liquor lignins.

RESULTS AND DISCUSSION

Based on literature results and general chemical considerations, it is clear that kraft pulp fibers retain a series of NPEs during kraft pulping due to metals complexation with lignin and carbohydrate functional groups. Although many lignin functional groups may be involved in this process, our previous studies had suggested that carboxylic acid groups and condensed phenolics might play an important role in the overall NPE binding process. To further examine the ability of lignin to complex and remove NPEs from kraft pulp fibers, we examined the intrinsic metal binding capacity of assorted kraft black liquor lignins. The black liquor lignins were isolated from a series of conventional and extended modified continuous kraft cooks. Table 1 summarizes some of the basic pulp properties and cooking parameters used to generate these lignin samples. The black liquor lignins were isolated from the liquors by acid precipitation and subsequently purified to remove all NPEs.

The metal binding capacity of black liquor lignin was initially evaluated by preparing a 2% consistency softwood kraft pulp slurry using a 0.10 N NaOH solution. To this solution was added a 5% charge of isolated black liquor lignin, and the resulting mixture was stirred for 4 hours at 25° and 80°C. Two black liquor lignin samples were employed for these studies. The first lignin sample was isolated from a conventional softwood 21 kappa kraft black liquor. The second lignin sample was isolated from an extended modified continuous softwood 21 kappa kraft black liquor. As a control, the same experiments were

TABLE 1
Summary of Kraft Pulping Parameters and Pulp Properties.

Cook Type	Kappa #	Viscosity (mPa · s)	Max Cook Temp. (°C)	H-factor	EA Charge During Impreg. (% NaOH on wood)	Sulfidity (%AA)	Total EA Consumed (% NaOH on wood)
Conv.	33	33	168.0	1200	21	30	15
Conv.	21	23	170.0	2000	21	30	15
Conv.	14	13	171.0	4000	21	30	17
Extended Modified	29	43	160.3	2000	10	30	14
Extended Modified	26	36	162.6	2400	10	30	15
Extended Modified	21	37	163.0	2500	10	30	18
Extended Modified	19	26	166.3	3400	10	30	15
Extended Modified	17	21	169.0	4100	10	30	16
Extended Modified	16	19	170.0	4500	10	30	17

repeated without the addition of black liquor lignin. The concentrations of Mn, Mg, and Ca were monitored before and after the chelation stage. Table 2 summarizes the initial concentration of these metals in the pulp prior to exposure to the 0.010 N NaOH solution.

TABLE 2
Initial Concentration of Metals in Brownstock Kraft Pulp.

Metal	30 kappa softwood kraft pulp	27 kappa softwood kraft pulp
Calcium	2000 ppm	1470 ppm
Magnesium	304 ppm	407 ppm
Manganese	79.3 ppm	25.7 ppm

Figure 2 summarizes the results of metals analysis of the pulp fibers after exposure to caustic with and without lignin at 25°. The results of these studies clearly demonstrate the ability of dissolved lignin to act as a “natural” chelant to remove metals from kraft pulps. Furthermore, these results indicate that the differences in pulping technology can influence the metal binding efficiency of black liquor lignins. Repeating the studies summarized in Figure 2 at 80°C resulted in comparable metal removal properties. This latter result suggests that the observed metal binding properties were obtained at equilibrium.

The metal binding properties of black liquor lignins were shown to be charge dependent. As shown in Figure 3, varying the charge of black liquor lignin from 2.5% to 10% at 25°C for 4 hours resulted in improved removal of metals from a kappa 30 softwood kraft pulp.

To further explore the metal binding capacity of black liquor lignins, a series of different black liquor lignin samples were evaluated for their metal binding capacity at 80°C using a softwood kraft pulp and the same procedures as described above. The results of these studies are summarized in Table 3.

TABLE 3
Metal Removal for Various Black Liquor Lignins¹ Applied to SW 27 Kappa Kraft Pulp at 80°C for 4 Hours.

Cook Type	Kappa #	Mn ²	Mg ²	Ca ²
Conventional	33	25%	21%	25%
Conventional	21	26%	22%	27%
Conventional	14	35%	29%	35%
Lo-Solids	29	30%	23%	26%
Lo-Solids	26	33%	22%	27%
Lo-Solids	21	31%	30%	33%
Lo-Solids	19	31%	23%	28%
Lo-Solids	17	39%	27%	31%
Lo-Solids	16	36%	28%	33%
Lo-Solids	11	41%	25%	29%

¹black liquor lignin was isolated from end of cook

²percentage of metal removed in addition to suspending and washing

The results of this analysis seem to reveal two possible trends. First, in general, the black liquor lignin samples from low kappa kraft pulps appear to be more efficient at removing lignin from pulp fibers than the lignin samples generated from higher kappa pulps. Secondly, it appears that the lignin samples from conventional versus extended modified continuous kraft cooks exhibit differences in metal binding properties. Further studies will be needed to confirm this latter suggestion.

Relationship Between Black Liquor Lignin Structure and Metal Binding Affinity

To explore the relationship between the structural features of lignin that may govern their metal binding properties we characterized the content of aliphatic hydroxyl groups, condensed and noncondensed phenoxy groups, and carboxylic acid groups in the black liquor lignins using standard NMR methods. Figure 4 illustrates the content of these functional groups in conventional black liquor lignin versus the metal removed from a kappa 27 SW kraft pulp. Based on this analysis the removal of Mn, Ca, and Mg from the SW kraft pulp appears to linearly correlate with the content of carboxylic acids and condensed phenolics. Interestingly, the linear correlation with phenolic and aliphatic hydroxyl group structures had a lower R^2 value. Also, the metal removal was not proportional to the content of free phenolics and aliphatic hydroxyl groups. A comparable analysis for the extended modified lignins did not exhibit a similar relationship between lignin functional groups and NPE removal. Several factors could be contributing to this effect. First, the end-of-cook extended modified lignins are different from the end-of-cook conventional lignins because the latter is a composite sample. In addition, the extended modified lignins represent only a fraction of the lignin released during pulping. Second, the molecular weight distributions of lignins from conventional kraft cooks differ from extended

modified kraft cooks.¹⁰ Differences in molecular weight distributions could well influence the NPE binding capacity of black liquor lignins.

CONCLUSIONS

In summary, we have demonstrated for the first time, the intrinsic NPE binding capabilities of black liquor lignins. We have observed differences in the NPE binding properties both as a function of extent of delignification and cooking technology employed. Furthermore, we have noted a potential correlation between the fundamental structure of black liquor lignins and their NPE binding capabilities. Clearly, additional studies will have to be completed to fully define these relationships.

The results of these studies suggest that the kraft digester could be employed to maximize NPE removal and simplify closed mill operations. Indeed, once these fundamental principles are fully understood, it may be possible to develop lignin extraction stages in a kraft digester that optimize the removal of NPEs during a kraft cook.

EXPERIMENTAL

Materials

All chemicals were commercially purchased and used as received except for p-dioxane, which was purified by distillation over sodium borohydride. All pulps were prepared from a single *Pinus taeda* tree grown in the southeastern part of the USA. The tree was debarked, chipped, and screened. On average, chip thickness varied between 2 - 8 mm.

Kraft Pulping

Kraft pulping experiments were performed at Ahlstrom Machinery on a laboratory scale using well-established procedures that simulate conventional and extended modified continuous (i.e., Lo-Solids[®]) cooking.^{11, 12, 13} Table 1 highlights some of the pulping parameters employed and physical pulp properties. All pulps used in this study were extensively washed with Nano-Pure water prior to usage.

Black Liquor Samples

The black liquor samples examined in this study were all end-of-cook samples. Hence, the black liquors from the conventional kraft cooks contain a composite mixture of lignin from throughout the cook. For the extended modified continuous kraft cooks, the end-of-cook black liquors are not a composite of all the lignin dissolved during the cook since the counter-current stage extracts black liquor.

Isolation of Lignin from Black Liquor

The procedure used for the isolation of lignin from black liquor was based upon literature methods.¹⁴ In brief, black liquor (50 mL, ~51 g) was diluted tenfold with distilled water and then treated with diethylenetriamine pentaacetic acid (DTPA, 0.3-0.4 g). This solution was stirred for one hour and then acidified to pH 2 with an aqueous 1.00 N HCl solution. The resulting suspension was frozen, thawed, centrifuged, and the supernatant decanted. The isolated lignin was then dispersed in nanopure water, and the DTPA chelation process was repeated. After acidification, the precipitated lignin was washed thoroughly with distilled water and then dissolved with a 9:1 *p*-dioxane:water solution. The aqueous *p*-dioxane solution was filtered, concentrated under reduced pressure, and

resulting precipitate was again treated with the DTPA chelation process. After acidification to pH 2, the precipitated lignin samples were washed thoroughly with distilled water and then freeze-dried. Finally, the lignin samples were Soxhlet extracted with pentane for 8 h and then dried under vacuum. ICP analysis of these lignins indicated that the metals Mn, Fe, Cu, Ba, Na, Mg, K, and Ca were nondetectable in the final purified form. The limit of detection was approximately 15 ppm for each metal.

Chelation Experiments

All of the chelation experiments were completed using two different temperatures (25°C and 80°C) and/or two different times (2 hours, 4 hours). All experiments were carried out in the same manner so as to reduce variation.

SW kraft pulp (5 g o.d., 30 or 27 kappa) and isolated lignin (250 mg) were added to a 500 mL Erlenmeyer flask. For the control experiments, no isolated lignin was added. A sodium hydroxide solution (0.01 N NaOH) was then preheated to the required temperature and added to the Erlenmeyer flask to make an approximately 5% consistency fiber suspension. The solution was then stirred for 30 seconds to disperse the fibers, and the consistency was further adjusted with 0.01 N NaOH to yield a final consistency of 2%. This flask was placed in a heated shaker at a pre-selected temperature of 25° or 80°C for 2 and 4 h. Upon completion, the pulps were washed with 500 mL 0.1 N NaOH, 500 mL 0.01 N NaOH, and 1000 mL of nanopure water. The pulps were then air dried and acid digested according to standard EPA procedures.¹⁵ The resulting matrix was then analyzed for Mn, Mg, and Ca concentration by inductively coupled plasma (ICP) spectrometry according to standard EPA procedures.¹⁶

Based on a series of replicate experiments, the experimental error associated with measuring the concentration of Mn, Mg, and Ca were ± 1.4 ppm, ± 4.8 ppm, and ± 23 ppm, respectively.

³¹P NMR Analysis of Black Liquor Lignins

Black liquor lignins (25 mg) were derivatized with 2-chloro-4,4,5,5-tetramethyl-1,3,2-dioxaphospholane (65 μ L) and analyzed by ³¹P NMR following literature procedures.^{17, 18}

REFERENCES

1. Edwards, L., Gu, Y., Jaegel, A., and Nepote, J., International Nonchlorine Bleaching Conference: Proceedings, Session Closing the Loop-Part 2, Paper no. 11-1 (1996).
2. Ulmgren, P., Nord. Pulp Pap. Res. J., 1(12), 32 (1997).
3. Lindberg, H., Engdahl, H., and Puumalainen, R., 1994 International Pulp Bleaching Conference, 293 (1994).
4. Edwards, L.L., Gu, Y., Hallen, R.T., Josephson, G.J., Lilga, M.A., Malmberg, B.J., Rick J., Rassat, S.D., and Sukanto, J.H., TAPPI Pulping Conference Proceedings, Book 2, 935 (1998).
5. Easty, D. B., Frederick, W.J., Jr., Malcolm, E.W., and Westervelt, H.H., Anal. Chim. Acta, 138, 237 (1982).
6. Axegard, P., Bergnor, E., Ek, M., and Ekholm, U., Tappi J., 79(1), 113 (1996).
7. Bryant, P., Edwards, L.L., Robarge, K., Tappi J., 76(10), 148 (1993).
8. Bryant, P.S., Edwards, L.L., J. Pulp Pap. Sci., 22(1), J37 (1996).
9. Werner, J.A., Ragauskas, A.J., Jian, J.E., TAPPI Pulping Conference Proceedings, Book 3, 1145 (1998).
10. Dong, D., Fricke, A.L., J. Wood Chem. Tech., 15(3), 369 (1995).
11. Marcoccia, B.S., Laakso, R., McClain, G., Tappi J., 79(6), 179 (1996).
12. Jiang, J.E., Greenwood, B.F., Philips, J.R., Stromberg, C.B., CTAPI 7th International Symposium on Wood Pulping Chemistry Proceedings, 1, 337 (1993).
13. Jiang, J.E., Herschmiller, D.W., TAPPI Pulping Conference Proceedings, 311 (1996).
14. Gellerstedt, G., Lindfors, E., Holz., 38(3), 151 (1984).
15. United States Environmental Protection Agency, Test Methods for Evaluating Solid Waste, p. 3050A-1-3050A-6, Office of Solid Waste and Emergency Response, SW-846 3rd edition, 1986.
16. United States Environmental Protection Agency, Test Methods for Evaluating Solid Waste, p. 6010A-1-6010A-16, Office of Solid Waste and Emergency Response, SW-846 3rd edition, 1986.
17. Granata, A., Argyropoulos, D., J. Ag. Food Chem., 43, 1538 (1995).
18. Werner, J.A., Ragauskas, A.J., Jian, J.E., AIChE Forest Products Symposium, accepted for publication (1998).

- FIGURE 1. Proposed NPE binding scheme involving carboxyl and condensed phenoxy groups.
- FIGURE 2. Percentage of metal removed from 27 kappa softwood kraft pulp at 25°C.
- FIGURE 3. Metal removal versus the amount of black liquor lignin added to SW kappa 30 kraft pulp at 25C for 4 hours.
- FIGURE 4. Metal removal versus the functional group content of conventional black liquor lignins applied to softwood kraft pulp at 80°C for 4 hours.









